



CONTACT ELEMENTS

Patent number: FR2232847
Publication date: 1975-01-03
Inventor:
Applicant: RINGSDORFF WERKE GMBH (DE)
Classification:
- **international:** *H01H1/025; H01H1/027; H01R39/20; H01H1/02; H01R39/00; (IPC1-7): H01R39/18*
- **european:** H01R39/20; H01H1/027
Application number: FR19740019703 19740607
Priority number(s): DE19732329698 19730609

Also published as:

 G B1438224 (A)
 DE 2329698 (A1)

Report a data error here

Abstract not available for FR2232847

Abstract of corresponding document: **GB1438224**

1438224 Contact element RINGSDORFF- WERKE GmbH 10 June 1974 [9 June 1973] 25723/74

Heading H2E [Also in Division C7] A contact element comprises graphite particles, preferred size range 0.01 to 0.15 mm., with a coating of metal, e.g. Cu or Ag preferably one tenth to one twentieth of particle size in thickness and 10 to 60% of weight of contact element, compressed to shape and heated in an inert or reducing atmosphere to at least partially sinter the metal coating. The metal preferably contains up to 1% by weight of one or more of the elements Cu, Al, Si, Mn, Fe, Zn, Mo, Ag, Cd, Sn or Pb and/or their oxides or sulphides to improve sintering. The coated particles may be mixed with carbon and/or graphite in powdered form and/or inorganic lubricant and polishing substances, e.g. molybdenum disulphide, cadmium sulphide and vitreous substances e.g. glass powder, as well as possibly metal powder, and/or a binder, e.g. a curable synthetic resin, prior to sintering. The metal coating may be applied by electroplating or electroless metallization or by vapour-coating in a fluidized bed.

Data supplied from the **esp@cenet** database - Worldwide